

SPECIFICATION:

Jaydex Single Sheet Membrane System with Plain Finish on Concrete

ROOFING SOLUTION

NOVA101C

AUG 2010

INTRODUCTION

This specification includes the preparation and application of the **Jaydex 4 mm Polibit Plain** single sheet system (ISO9001) to a concrete roof. The system is composed of 4 mm plain finished membrane torch applied direct to the substrate surface. The **Jaydex Polibit Plain** membrane possesses strong polyester reinforcement. This strong, thick membrane system is subsequently overcoated where it will be left permanently exposed during its service life. It can be pedestrian trafficked for maintenance purposes.

Note: Jaydex (*only*) supply APP / (Atatic Polypropylene) Polyester reinforced membranes.

SUBSTRATE PREPARATION

Concrete shall be correctly formed to falls and adequately cured, all ridges protrusions stone flush and all depressions gauge patched with modified sand cement. Concrete to be finished to NZS3114:1980 U2. Only wood or bull float manually to create an even surface finish (no power floats are to be utilised)

Timber fillets 20mm x 20mm minimum shall be installed at all vertical and horizontal junctions. Falls to be a 1:30 minimum for Roof Areas and 1 in 100 minimum for any associated Internal Gutters as per E2/AS1.

APPLICATION OF MEMBRANE SYSTEM

Primer

One coat of Bitumen Primer is applied at a spreading rate of approx 8sqm/litre by brush or roller over total roof area and allowed to dry.

Membrane to Roofs

All internal and external corners and vertical to horizontal transitions shall have plain membrane gusset patches and strips applied before the main membrane application is applied over the total roof gutter area.

Torch down the **Jaydex Polibit Plain** polyester reinforced plain membrane to the preprimed substrate. Torch seal separately all end and side joints to ensure correct closure. All joints are torch sealed separately to ensure correct closure.

Membrane to Gutters

Where internal gutters form part of the roof area. **Jaydex Polibit Plain** 3 mm membrane can be substituted for the **Jaydex Polibit Plain** 4 mm membrane. It is torch applied first before the main roof membrane application commences.

Overcoating

Any **Jaydex Polibit Plain** membrane area left exposed permanently is to be overcoated with **Jaydex Colour – It barrier coat** followed by a two coat application of **Jaydex Aquaseal** an acrylic sealer with optional colour choice. Alternately a two coat application of **Jaydex Alumicote** can be applied to create a reflective silvery finish to the exposed membrane Roof Area.

For Potable water requirements please refer to our **Specification NOVA141** and /or contact Jaydex

Allow adequate curing time between all coats.

ROOF VENTS

For top ventilating of enclosed cavities below rooflines. Jaydex possess low profile tough light efficient **Air Vents** that can be installed down to a minimum of 20sqm of roof surface area per vent to release potential hot moist air build ups. Ventilation methodology is the sole responsibility of the Designer – Contact Jaydex

DRAINAGE OUTLETS

Jaydex possess Outlets of tough light composition and of various aperture sizing. These units incorporating flanges to ensure watertightness can drain water away through parapets, deck/roof inverts and from internal gutters. Jaydex also possess sump units to cater for both the overflow and outlet function in the same unit

MAINTENANCE

- 1** The Jaydex Membrane Roof/Deck system, must be regularly checked for damage by others. Any damage, detected must be correctly repaired and where applicable a recoat carried out over the membrane. All rubbish / debris left lying on the membrane surface must be removed.
- 2** Jaydex Side and Dropper drainage units must be regularly checked with removal of any accumulated rubbish at the inlets. All inlets should have Jaydex propriety grates installed in them.
- 3** Jaydex recommend a periodic clean down with water; (plus 1 percent soap) of all exposed Membrane Roof / Deck Surfaces in conjunction with a Moss Inhibiter.

WARRANTY

When Jaydex Licensed Contractors apply this membrane system in accordance with this specification a Standard Warranty will be issued for up to twenty (25) years.